



"Metal processing technology" LLC

Production testing laboratory

Ergashev J.K

"05"01.2025

TEST REPORT

SOFT ANNEALED COILS

Manufacture Size				Mass per m/kg	Rated internal working pressure (bar/psi)
mm		Inches			
OD	WT	OD	WT		
19,05	1,07	3/4"	0,042	0,5387	180/2610,68
22,23	1,14	7/8"	0,045	0,6732	183/2654,19
28,58	1,27	1-1/8"	0,050	0,9711	176/2552,66
34,92	1,40	1-3/8"	0,055	1,3140	190/2755,72
41,27	1,52	1-5/8"	0,059	1,6918	201/2915,26
9,53	0,61	3/8"	0,024	0,1524	120/1740,46
12,70	0,71	1/2"	0,028	0,2384	150/2175,57
15,88	0,71	5/8"	0,028	0,3016	148/2146,56
15,88	1,02	5/8"	0,040	0,4244	175/2538,16
6,35	0,76	1/4"	0,030	0,1190	142/2059,54
12,70	0,81	1/2"	0,032	0,2697	165/2393,12
15,88	0,89	5/8"	0,035	0,3736	154/2233,58

The test results only apply to the samples submitted for testing.

Responsible for the test:

Laboratory technician:



Xolmurodov A