

"Metal processing technology" LLC



Production testing laboratory

Ergashev JK

"05"01.2025

TEST REPORT

| Manufacture Size | | | | Mass per m/kg | Rated internal working pressure (bar/psi) |
|------------------|------|--------|-------|---------------|--|
| mm | | Inches | | | |
| OD | WT | OD | WT | | |
| 19,05 | 1,07 | 3/4" | 0,042 | 0,5387 | 210/ 3045,79 |
| 22,23 | 1,14 | 7/8" | 0,045 | 0,6732 | 195/ 2828,24 |
| 28,58 | 1,27 | 1-1/8" | 0,050 | 0,9711 | 190/ 2755,72 |
| 34,92 | 1,40 | 1-3/8" | 0,055 | 1,3140 | 200/ 2900,75 |
| 41,27 | 1,52 | 1-5/8" | 0,059 | 1,6918 | 230/ 3335,87 |
| 9,53 | 0,61 | 3/8" | 0,024 | 0,1524 | 150/ 2175,57 |
| 12,70 | 0,71 | 1/2" | 0,028 | 0,2384 | 160/ 2320,6 |
| 15,88 | 0,71 | 5/8" | 0,028 | 0,3016 | 155/ 2248,08 |
| 15,88 | 1,02 | 5/8" | 0,040 | 0,4244 | 195/ 2828,24 |
| 6,35 | 0,76 | 1/4" | 0,030 | 0,1190 | 160/ 2320,6 |
| 12,70 | 0,81 | 1/2" | 0,032 | 0,2697 | 190/ 2755,72 |
| 15,88 | 0,89 | 5/8" | 0,035 | 0,3736 | 180/ 2610,68 |

The test results only apply to the samples submitted for testing.

Responsible for the test:

Laboratory technician:



Ergasheva M